










OAKLANDS COLLECTION CONSTRUCTION SPECIFICATION

	CONSTRUCTION MACHINE GAUGE PILE HEIGHT TUFT DENSITY PILE WEIGHT TOTAL CARPET WEIGHT CARPET THICKNESS WIDTH	32 1/10th Gauge 5.8 mm 131,750 tufts/m ² 1,085 gms/m ² 32 oz/yd ² 2,022 gms/m ² 8.5 mm 4 & 5 metre	42 1/10th Gauge 6.8 mm 158,875 tufts/m ² 1,424 gms/m ² 42 oz/yd ² 2,360 gms/m ² 9.4 mm 4 & 5 metre	50 1/10th Gauge 7.8mm 162,750 tufts/m ² 1,695 gms/m ² 50 oz/yd ² 2,632 gms/m ² 10.4 mm 4 & 5 metre
	COMPOSITION PILE CONTENT PRIMARY BACKING SECONDARY BACKING	ISO 1833 80% Pure New Wool 10% Polypropylene 10% Tuftbond Woven Polypropylene Woven Secondary	80% Pure New Wool 10% Polypropylene 10% Tuftbond Woven Polypropylene Woven Secondary	80% Pure New Wool 10% Polypropylene 10% Tuftbond Woven Polypropylene Woven Secondary
 EHD  MC	PERFORMANCE SUITABILITY WIRA ABRASION TEST STATIC LOADING DYNAMIC LOADING TUFT ANCHORAGE	Heavy Domestic Exceeds 20,000 Rubs 27.1% Thickness loss after 24 hrs recovery 36.8% Thickness loss after 1,000 impacts Above 1kg	Extra Heavy Domestic Exceeds 27,000 Rubs 21.3% Thickness loss after 24 hrs recovery 28.4% Thickness loss after 1,000 impacts Above 1kg	Extra Heavy Domestic Medium Contract Exceeds 30,000 Rubs 23.3% Thickness loss after 24 hrs recovery 27.3% Thickness loss after 1,000 impacts Above 1kg
	COLOUR FASTNESS LIGHT FASTNESS WET FASTNESS SHAMPOO FASTNESS	ISO 105-B02 ISO 105-E01 BS 1006:UK-TB 6 on all colours 4/5 on all colours 4/5 on all colours	6 on all colours 4/5 on all colours 4/5 on all colours	6 on all colours 4/5 on all colours 4/5 on all colours
	THERMAL VALUE TOG VALUE THERMAL RESISTANCE	ISO 5085-1 1.2 Tog 0.12 m ² k/w	1.4 Tog 0.14 m ² k/w	1.5 Tog 0.15 m ² k/w
	FLAMMABILITY CE CE MARK RATING HOT METAL NUT TEST METHENAMINE PILL TEST	Dfl, S1 Pass - Low radius of ignition Pass	Dfl, S1 Pass - Low radius of ignition Pass	Dfl, S1 Pass - Low radius of ignition Pass
	CHEMICAL IMPACT CE FORMALDEHYDE REACH CERTIFICATE	E1 Compliant	E1 Compliant	E1 Compliant
	BIOLOGICAL ATTACK MOTH / INSECT RESISTANT	Eulan Treated	Eulan Treated	Eulan Treated

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear. These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

Heather Shades - In manufacturing heather shades several contrasting colours are blended to create a 'heather' yarn. As such random coloured flecks will be apparent in the carpet. These flecks form part of the effect and are not considered the basis for any claim.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.

March 2016



GREENWOOD & COOPE LTD. Brookhouse Mill, Greenmount, Bury, Lancashire BL8 4HR
 TEL: 01204 881234 FAX: 01204 887722
 E-MAIL: info@cormarcarpets.co.uk WEBSITE: www.cormarcarpets.co.uk

